



Technical Data Sheet

CM Mask 2-104

PRODUCT DESCRIPTION CM Mask 2-104 is a UV / Visible light curable masking material that provides excellent surface protection of rough or porous components during mild to moderate surface finishing processes such as grit blasting, shot peening, and polishing. This flexible, high adhesion mask is ideal for protecting steel, aluminum, titanium, cobalt, and other commonly used metals in the aerospace and medical implant industries. CM Mask 2-104 contains no nonreactive solvents and cures when exposed to light. After processing, it is easily removed by peeling.

UNCURED PROPERTIES

COMPOSITION	Urethane Acrylate / Monomer Blend
VISCOSITY	20,000 cP
APPEARANCE	Green Thixotropic Gel
SPECIFIC GRAVITY	1.1 -1.2 at 25 ⁰ C.
FLASH POINT	200 ⁰ F.
TOXICITY	Refer to Material Safety Data Sheet
SHELF LIFE	One Year

CURED PROPERTIES

DUROMETER	Shore D 25
WATER ABSORPTION	< 1% (24 hour immersion)
TEMPERATURE RANGE	-45 ⁰ C. – 145 ⁰ C.

CURING INFORMATION

<u>UV Intensity</u>	<u>Thickness</u>	<u>Time to Cure</u>
100 mW/cm ²	2 mm	30 seconds

THESE ARE TYPICAL PROPERTIES AND ARE NOT MEANT TO BE PRODUCT SPECIFICATIONS.

Composition Materials Technical Data Sheet

CM MASK 2-104

Storage – This is light sensitive material. Containers must remain covered when not in use. Minimize exposure of uncured material to daylight, artificial light, and UV light during storage and handling. Store uncured product in its original, closed container in a dry location. Unless otherwise indicated on the product label, optimal storage temperatures are 10 to 30°C, (50 to 86°F). Any material removed from the original container must not be returned to the container as it could be contaminated. Composition Materials cannot assume responsibility for products that were improperly stored, contaminated, or repackaged into other containers.

Handling and Clean-Up – For safe handling information, consult this product's Material Safety Data Sheet (MSDS) prior to use. Uncured material may be wiped away from surfaces with organic solvents. Do not use solvents to remove material from eyes or skin!

Using the Product – Prior to dispensing, ensure that each surface coming in contact with this product is clean and free of grease, mold release, or other contaminants. Dispense directly from the package, or utilize appropriate dispensing equipment that is compatible with light-curable adhesives and coatings. Fluid lines and dispense tips must be 100% light blocking. Curing stations should be equipped with air exhaust systems to evacuate vapors and heat generated during the curing process. After curing, this product must be allowed to cool to ambient temperature before testing the product's performance.

THE VALUES NOTED IN THIS TECHNICAL DATA SHEET ARE TYPICAL PROPERTIES AND ARE NOT MEANT TO BE USED AS PRODUCT SPECIFICATIONS. The information contained in this data sheet is believed to be accurate and is provided for information only. Composition Materials Co., Inc. makes no representation or warranties of any kind concerning this information. **It is the user's responsibility to determine the suitability of this product for any intended use.** Composition Materials Co., Inc. does not assume responsibility for test or performance results obtained by the user. The user assumes all risk and liability connected with the use of this product. The user should adopt such precautions and use guidelines as may be advisable for the protection of property and persons against any hazards that may be involved in this product's handling or use. Composition Materials Co., Inc. specifically disclaims any liability for consequential or incidental damages of any kind arising from the handling or use of this product. The information contained in this Technical Data Sheet offers no assurance that the product use, application, or process will not infringe on existing patents or licenses of others. Nothing in this Technical Data Sheet transfers or grants license for the use of any patents, tradeseecrets, intellectual property, or confidential information that is the property of Composition Materials Co., Inc.

Revision September, 2012