COMPOSITION MATERIALS CO., INC.







Walnut Shell Products

WALNUT SHELL COSMETIC-GRADE

Exfoliation • Scrubs • Soaps • Body Washes • Personal Care Products • Microbead Replacement

TYPICAL PROPERTIES				
APPEARANCE	Brown, granular			
FLASH POINT	380° F			
CHARRING TEMPERATURE	470° F			
SPECIFIC GRAVITY	1.2 - 1.4			
HARDNESS	MOH 3.5 • Rockwell 91 • Brinell 190			
PH AT 25°C in neutral H₂O	4-6			
FREE MOISTURE 80°C 15 Hrs	3-11%			
DRY PACKING DENSITY	22 - 53 lbs./cu. ft.			

CHEMICAL ANALYSIS				
NITROGEN	0.10%			
CELLULOSE	40 - 60%			
LIGNIN	20 - 30%			
TOLUENE SOLUBILITY	0.5 - 1.0%			
CHLORINE	.10%			
ASH	1.5%			
CUTIN	1.0%			
NITROGEN	0.10%			

STANDARD SIEVE SPECIFICATIONS (% THROUGH SCREEN)					
PRODUCT U.S. Screen	AD-7B 35/60	AD-9B 40/100	AD-10.5B 60/200		
#20 MESH	99% (min)				
#30 MESH		99.9% (min)			
#35 MESH	88% (min)				
#40 MESH		90% (min)	99.9% (min)		
#50 MESH					
#60 MESH	15% (max)		80% (min)		
#100 MESH	1% (max)	10% (max)			
#200 MESH		2% (max)	10% (max)		

				_
РΔ	CK	ΔG	IIN	Œ

50 lb. Bags - Pallets (40 bags per pallet) - Supersacks (2,000 lbs.) - 200 lb. Drums - 50 lb. Drums

